

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Bremworth
7 Grayson Avenue
Papatoetoe
Auckland 2104 New Zealand

Test Number : 22-003153
Issue Date : 28/10/2022
Print Date : 28/10/2022

Sample Description Clients Ref : "The Hamptons 830"
Tufted cut pile carpet
Colour : Lt Brown



281561

59968

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Bremworth
7 Grayson Avenue
Papatoetoe
Auckland 2104 New Zealand

Test Number : 22-003153
Issue Date : 28/10/2022
Print Date : 28/10/2022

ASTM C518-2021

Steady-State Thermal Transmission Properties by Means of the Heat Flow Apparatus

Test Date	27-10-2022	
Test Apparatus	Lasercomp Fox 314	
Sample Orientation	Horizontal	
Heat Flow Direction	Up	
Mean Test Temperature	23 °C	
Temperature Differential	20 °C	
Average Thermal Gradient	353.8 K/m	
Estimated uncertainty in results	3.1 %	
Specimen	1	2
Specimen Thickness (as received)	11	11 mm
Specimen Thickness (as tested)	57	56 mm
Specimen Density (as tested)	282	288 kg/m ³
Test Duration	01:04	01:26 hrs:mins
Measured Heat Flux	24.8	24.4 W/m ²
Measured Thermal Conductance	1.2376	1.2216 W/m ² K
Measured Thermal Conductivity	0.0703	0.0688 W/m.K
Thermal Resistance	0.81	0.82 m ² K/W
Thermal Resistance (1 layer)	0.16	0.16 m ² K/W

The calibration of the Heat Flow Apparatus was checked immediately prior to the commencement of the test.

Each specimen was a pile of 5 layers of carpet placed face to back.

281561

59968

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR